

切削参数参考表
Recommended Milling Conditions

加工材料 Work Material		高硬度钢 Hardened Steels STAVAX・SKD61 (~52HRC)				高硬度钢 Hardened Steels SKD11・ELMAX (~62HRC)				高速钢 High Speed Steels SKH・HAP (~68HRC)			
(R)球头半径 Radius	颈长 Under Neck Length	切深量 Depth of Cut		进给速度 Feed	主轴转速 Spindle Speed	切深量 Depth of Cut		进给速度 Feed	主轴转速 Spindle Speed	切深量 Depth of Cut		进给速度 Feed	主轴转速 Spindle Speed
		ap mm	ae mm	mm/min	min ⁻¹	ap mm	ae mm	mm/min	min ⁻¹	ap mm	ae mm	mm/min	min ⁻¹
0.1	1	0.005	0.005	200	40,000	0.005	0.005	150	40,000	0.003	0.003	100	40,000
	0.9	0.005	0.005	600	40,000	0.005	0.005	400	40,000	0.003	0.005	300	40,000
0.15	1.5	0.005	0.005	320	40,000	0.005	0.005	240	40,000	0.003	0.005	160	40,000
	2	0.005	0.01	500	40,000	0.005	0.01	400	40,000	0.005	0.005	320	40,000
0.2	3	0.005	0.005	250	40,000	0.005	0.005	200	40,000	0.003	0.005	120	40,000
	1.5	0.01	0.01	1,200	40,000	0.01	0.01	1,000	40,000	0.005	0.01	600	40,000
0.25	2.5	0.01	0.01	720	40,000	0.01	0.01	600	40,000	0.005	0.01	480	40,000
	3.5	0.01	0.01	400	36,000	0.005	0.01	320	36,000	0.005	0.005	240	36,000
0.3	3	0.01	0.02	1,200	40,000	0.01	0.02	800	40,000	0.01	0.01	600	40,000
	4	0.01	0.01	540	36,000	0.01	0.01	400	36,000	0.005	0.01	320	36,000
	5	0.01	0.01	360	30,000	0.005	0.01	320	30,000	0.005	0.005	240	30,000
	6	0.005	0.005	240	24,000	0.005	0.005	200	24,000	0.003	0.003	160	24,000
0.4	4	0.01	0.015	1,000	40,000	0.01	0.015	800	40,000	0.005	0.01	600	40,000
	6	0.005	0.01	720	30,000	0.005	0.01	540	30,000	0.005	0.005	400	30,000
0.5	4	0.02	0.03	1,600	40,000	0.02	0.02	1,200	40,000	0.01	0.015	800	40,000
	6	0.015	0.02	1,200	30,000	0.015	0.015	900	30,000	0.01	0.01	600	30,000
	8	0.01	0.015	720	20,000	0.01	0.01	540	20,000	0.005	0.01	400	20,000
0.6	10	0.01	0.01	540	16,000	0.005	0.01	400	16,000	0.005	0.005	300	16,000
	6	0.02	0.02	1,400	32,000	0.015	0.02	1,000	32,000	0.01	0.015	720	32,000
0.75	7.5	0.02	0.03	1,600	32,000	0.015	0.03	1,400	32,000	0.01	0.01	1,000	32,000
	10	0.015	0.02	900	20,000	0.01	0.02	720	20,000	0.01	0.01	540	20,000
	15	0.01	0.02	480	12,000	0.01	0.01	400	12,000	0.005	0.01	300	12,000
1	6	0.03	0.05	2,400	40,000	0.03	0.03	2,000	40,000	0.02	0.02	1,600	40,000
	8	0.03	0.03	2,000	36,000	0.02	0.03	1,400	36,000	0.01	0.02	1,000	36,000
	10	0.02	0.03	1,600	32,000	0.015	0.03	800	32,000	0.01	0.015	600	32,000
	14	0.02	0.02	900	20,000	0.01	0.02	720	20,000	0.01	0.01	540	20,000
20	20	0.02	0.02	360	8,000	0.01	0.02	320	8,000	0.01	0.01	240	8,000
备 注 Notes		※1 切深量为中精加工、精加工时的最大值。请根据机床刚性和要求精度进行调整。 ※2 预加工（中精加工）时请注意精加工余量相对于加工面需保持均匀。 ※3 发生振刀时，请以相同的比率降低主轴转速和进给速度。此外，主轴转速过低时，也以相同的比率降低。 ※4 R角等负载大的加工部位，请特别注意参数设定和刀路轨迹等。 ※5 加工深沟时，请充分注意冷却液的供油及排屑是否顺畅。 ※6 建议使用油雾冷却方式。 ※1 Max. Depth of Cut for semi-finishing and finishing. Adjust milling conditions depending on the rigidity of the machine and desired accuracy. ※2 Obtain uniform stock amount on the cutting surface in the pre-stage cutting (semi-finishing). ※3 Reduce both spindle speed and feed at same rate for chattering and also for insufficient spindle speed of a machine. ※4 Required careful set up of milling conditions, tool path and etc. at cutting parts, such as corners where will become overloaded. ※5 Coolant supply and chip disposal in the deep portion are very important. ※6 Oil mist coolant is recommended.											



无涂层
Non-Coating

- H ~52高硬度钢
HRC Hardened Steel
- H ~60高硬度钢
HRC Hardened Steel
- H ~65高硬度钢
HRC Hardened Steel
- H ~70高硬度钢
HRC Hardened Steel

使用注意事项

加工环境 Advice on Cutting Environment

- 刀具偏摆量越小越好。
Minimize the deflection of cutting edge.
- 掌握机床主轴的伸缩量以及机床的水平状态，需要时采取恰当的措施。
To understand the nature of the expansion of the main spindle and machine posture transformation, and take measures against them.

精加工量(余量) Advice on Finishing Allowance (stock amount)

- 使用小径CBN铣刀时，精加工量(余量)均匀性非常重要。
When using small CBN End Mill, uniform finishing allowance (stock amount) is important.
- 粗加工・中精加工使用刀具磨损过大时，中精加工和精加工的余量会变大，从而影响刀具寿命和加工精度，所以预加工时留有均匀的加工余量非常重要。
When tool is used on roughing and semi-finishing and it has a big abrasion, finishing allowance (stock amount) on semi-finishing and finishing is increasing and it affects tool life and cutting accuracy. Therefore, it is important to get uniform stock amount in the pre-stage cutting.

Points in Use

工件顶部 Top of work material
中精加工表面 Surface for semi-finishing
最终精加工表面 Surface for finishing
注意R角部位! No uniformity at corner area

CBN
核心系列
CBN
Core Line