



切削参数参考表

Recommended Milling Conditions

加工材料 Work Material		碳素钢·合金钢* ₁ ·不锈钢* ₁ Carbon Steels·Alloy Steels* ₁ ·Stainless Steels* ₁ S50C·SCM* ₁ ·SKD* ₁ ·SUS* ₁			调质钢 Prehardened Steels NAK55·NAK80·HPM1 (~43HRC)			铜合金·铝合金 Copper·Aluminium Alloy		
外径 Dia.	颈长 Under Neck Length	主轴转速 Spindle Speed	进给速度 Feed	切深量 Depth of Cut	主轴转速 Spindle Speed	进给速度 Feed	切深量 Depth of Cut	主轴转速 Spindle Speed	进给速度 Feed	切深量 Depth of Cut
		min ⁻¹	mm/min	ap mm	min ⁻¹	mm/min	ap mm	min ⁻¹	mm/min	ap mm
0.1	0.3	40,000	150	0.005	40,000	120	0.004	40,000	150	0.006
	0.5	40,000	100	0.004	40,000	75	0.003	40,000	100	0.005
	0.75	40,000	60	0.003	40,000	50	0.002	40,000	60	0.003
	1	40,000	40	0.002	40,000	30	0.002	40,000	40	0.002
0.15	0.3	40,000	200	0.005	40,000	150	0.004	40,000	200	0.008
	0.5	40,000	150	0.005	40,000	120	0.004	40,000	150	0.008
	0.75	40,000	100	0.004	40,000	90	0.003	40,000	100	0.006
	1	40,000	80	0.003	40,000	60	0.002	40,000	80	0.004
	1.5	40,000	50	0.002	35,000	40	0.002	40,000	50	0.003
0.2	0.5	40,000	330	0.01	40,000	250	0.007	40,000	330	0.012
	0.75	40,000	280	0.008	40,000	220	0.006	40,000	280	0.01
	1	40,000	250	0.007	40,000	180	0.005	40,000	250	0.008
	1.5	40,000	180	0.005	35,000	120	0.004	40,000	180	0.006
	2	40,000	100	0.003	35,000	65	0.002	40,000	100	0.004
	2.5	35,000	80	0.003	30,000	50	0.002	40,000	90	0.003
	3	30,000	60	0.002	25,000	40	0.002	35,000	70	0.002
	3.5	25,000	40	0.002	22,000	30	0.002	30,000	50	0.002
	4	23,000	30	0.001	20,000	20	0.001	25,000	35	0.001
0.3	1	40,000	400	0.02	35,000	260	0.015	40,000	400	0.024
	1.5	40,000	350	0.015	35,000	230	0.01	40,000	350	0.018
	2	35,000	300	0.01	30,000	180	0.007	40,000	320	0.012
	2.5	30,000	250	0.007	25,000	160	0.005	35,000	280	0.008
	3	30,000	200	0.005	25,000	130	0.004	35,000	250	0.006
	4	25,000	120	0.004	22,000	80	0.003	30,000	150	0.004
	5	22,000	80	0.003	20,000	55	0.002	25,000	90	0.003
	6	20,000	60	0.002	18,000	40	0.002	22,000	65	0.002
0.4	9	18,000	30	0.001	16,000	20	0.001	20,000	35	0.001
	1	35,000	500	0.025	30,000	330	0.018	40,000	600	0.03
	1.5	35,000	450	0.02	30,000	280	0.014	40,000	500	0.026
	2	35,000	400	0.02	30,000	260	0.014	40,000	450	0.024
	2.5	30,000	350	0.015	25,000	230	0.01	40,000	400	0.02
	3	30,000	300	0.015	25,000	190	0.01	35,000	350	0.018
	3.5	25,000	250	0.01	25,000	160	0.008	35,000	280	0.015
	4	25,000	200	0.01	22,000	140	0.007	30,000	240	0.012
	5	22,000	160	0.008	20,000	110	0.005	25,000	180	0.01
	6	20,000	120	0.005	18,000	80	0.003	22,000	130	0.006
	7	18,000	100	0.003	16,000	70	0.002	20,000	110	0.003
	8	18,000	80	0.002	16,000	60	0.002	20,000	85	0.002
0.5	9	18,000	70	0.002	16,000	50	0.002	20,000	75	0.002
	10	18,000	60	0.002	16,000	40	0.002	20,000	65	0.002
	12	18,000	40	0.002	16,000	30	0.002	20,000	45	0.002
	1	30,000	550	0.03	25,000	350	0.022	35,000	650	0.036
	1.5	30,000	520	0.028	25,000	330	0.02	35,000	630	0.033
	2	30,000	500	0.025	25,000	320	0.018	35,000	600	0.03
	2.5	30,000	470	0.023	25,000	290	0.016	35,000	580	0.027
	3	30,000	450	0.02	25,000	280	0.014	35,000	550	0.024
	3.5	30,000	420	0.018	22,000	250	0.012	30,000	500	0.021
	4	25,000	350	0.015	22,000	230	0.01	30,000	420	0.018
	4.5	25,000	320	0.013	20,000	200	0.008	30,000	380	0.015
	5	25,000	300	0.01	20,000	180	0.007	30,000	350	0.012

*1 切削合金钢、不锈钢时，请将主轴转速及进给速度降低至80%时的值作为参考值。

*1 Reference value for Alloy and Stainless Steels are 80% of recommended cutting conditions.

P 碳素钢
Carbon SteelP 合金钢
Alloy SteelP 调质钢
Prehardened SteelH ~52高硬度钢
HRC Hardened SteelM 不锈钢
Stainless SteelN 铝合金
Aluminium AlloyN 铜合金
CopperO 树脂
Resin

常规系列
无限涂层
长颈造型
Regular Line
MUGEN COATING
Long Neck Type

MHR230

切削参数参考表

Recommended Milling Conditions

加工材料 Work Material		碳素钢・合金钢* ₁ ・不锈钢* ₁ Carbon Steels・Alloy Steels* ₁ ・Stainless Steels* ₁ S50C・SCM* ₁ ・SKD* ₁ ・SUS* ₁			调质钢 Prehardened Steels NAK55・NAK80・HPM1 (~43HRC)			铜合金・铝合金 Copper・Aluminium Alloy		
外径 Dia.	颈长 Under Neck Length	主轴转速 Spindle Speed	进给速度 Feed	切深量 Depth of Cut	主轴转速 Spindle Speed	进给速度 Feed	切深量 Depth of Cut	主轴转速 Spindle Speed	进给速度 Feed	切深量 Depth of Cut
		min ⁻¹	mm/min	ap mm	min ⁻¹	mm/min	ap mm	min ⁻¹	mm/min	ap mm
0.5	6	20,000	200	0.008	18,000	140	0.005	25,000	250	0.01
	7	20,000	180	0.005	16,000	110	0.003	22,000	200	0.006
	8	18,000	150	0.003	14,000	90	0.002	20,000	160	0.003
	9	16,000	120	0.003	14,000	80	0.002	18,000	135	0.003
	10	16,000	100	0.002	14,000	65	0.002	18,000	110	0.002
	12	16,000	80	0.002	14,000	50	0.002	18,000	90	0.002
	15	16,000	50	0.002	14,000	35	0.002	18,000	55	0.002
0.6	1.5	30,000	600	0.035	25,000	400	0.025	35,000	700	0.04
	2	30,000	600	0.035	25,000	380	0.025	35,000	700	0.04
	3	30,000	550	0.03	25,000	350	0.02	35,000	650	0.035
	4	25,000	450	0.025	22,000	300	0.018	30,000	550	0.03
	5	25,000	400	0.02	20,000	240	0.014	30,000	480	0.024
	6	20,000	300	0.015	18,000	200	0.01	25,000	380	0.018
	7	20,000	250	0.012	16,000	150	0.008	22,000	280	0.014
	8	18,000	200	0.01	15,000	130	0.007	20,000	230	0.012
	9	18,000	180	0.008	15,000	110	0.005	20,000	200	0.009
	10	16,000	150	0.005	14,000	100	0.003	18,000	170	0.006
	12	14,000	120	0.003	12,000	80	0.002	16,000	130	0.003
	15	14,000	90	0.002	12,000	60	0.002	16,000	100	0.002
0.7	18	14,000	60	0.002	12,000	40	0.002	16,000	70	0.002
	2	30,000	650	0.04	25,000	400	0.03	35,000	750	0.05
	4	25,000	500	0.03	22,000	330	0.02	30,000	600	0.04
	6	20,000	350	0.02	18,000	240	0.015	25,000	450	0.03
	8	18,000	280	0.015	15,000	180	0.01	22,000	350	0.02
	10	16,000	220	0.008	14,000	150	0.005	20,000	280	0.01
0.8	3	25,000	700	0.05	22,000	500	0.03	35,000	850	0.06
	4	25,000	600	0.045	22,000	400	0.03	30,000	720	0.055
	5	22,000	500	0.035	20,000	350	0.025	30,000	650	0.05
	6	20,000	450	0.03	18,000	300	0.02	25,000	560	0.04
	8	18,000	350	0.02	15,000	240	0.015	22,000	430	0.025
	10	16,000	300	0.01	14,000	200	0.007	20,000	380	0.012
	12	14,000	250	0.008	12,000	170	0.005	16,000	290	0.01
	14	12,000	200	0.005	10,000	140	0.003	14,000	230	0.006
	16	12,000	150	0.003	10,000	110	0.002	14,000	170	0.003
	20	12,000	120	0.002	10,000	80	0.002	14,000	140	0.002
	24	12,000	80	0.002	10,000	50	0.002	14,000	90	0.002
0.9	4	25,000	900	0.05	22,000	600	0.035	30,000	1,000	0.06
	6	20,000	600	0.04	18,000	400	0.03	25,000	750	0.05
	8	18,000	500	0.03	16,000	330	0.02	22,000	620	0.04
	10	16,000	400	0.02	14,000	260	0.015	20,000	500	0.025
	12	14,000	300	0.01	12,000	200	0.008	16,000	400	0.015
	15	12,000	250	0.008	10,000	160	0.005	14,000	300	0.01
1	2	25,000	1,500	0.07	22,000	1,000	0.06	30,000	1,800	0.08
	3	25,000	1,200	0.06	22,000	800	0.05	30,000	1,500	0.07
	4	25,000	1,100	0.055	22,000	700	0.045	30,000	1,300	0.065
	5	22,000	900	0.05	20,000	600	0.04	27,000	1,100	0.06
	6	20,000	800	0.045	18,000	500	0.035	25,000	1,000	0.055
	7	20,000	800	0.04	18,000	500	0.03	25,000	1,000	0.05
	8	18,000	700	0.035	15,000	400	0.025	22,000	850	0.045
	9	18,000	700	0.03	15,000	400	0.02	22,000	850	0.04

*1 切削合金钢、不锈钢时，请将主轴转速及进给速度降低至80%时的值作为参考值。

*1 Reference value for Alloy and Stainless Steels are 80% of recommended cutting conditions.



切削参数参考表

Recommended Milling Conditions

加工材料 Work Material		碳素钢・合金钢 ^{*1} ・不锈钢 ^{*1} Carbon Steels・Alloy Steels ^{*1} ・Stainless Steels ^{*1} S50C・SCM ^{*1} ・SKD ^{*1} ・SUS ^{*1}			调质钢 Prehardened Steels NAK55・NAK80・HPM1 (~43HRC)			铜合金・铝合金 Copper・Aluminium Alloy		
外径 Dia.	颈长 Under Neck Length	主轴转速 Spindle Speed	进给速度 Feed	切深量 Depth of Cut	主轴转速 Spindle Speed	进给速度 Feed	切深量 Depth of Cut	主轴转速 Spindle Speed	进给速度 Feed	切深量 Depth of Cut
		min ⁻¹	mm/min	ap mm	min ⁻¹	mm/min	ap mm	min ⁻¹	mm/min	ap mm
1	10	16,000	600	0.025	14,000	350	0.018	20,000	750	0.03
	12	14,000	500	0.02	12,000	300	0.014	18,000	650	0.025
	14	13,000	400	0.015	11,000	250	0.01	15,000	450	0.018
	16	12,000	300	0.01	10,000	200	0.007	14,000	350	0.012
	18	12,000	250	0.008	10,000	150	0.005	14,000	300	0.01
	20	11,000	200	0.005	9,000	120	0.003	13,000	230	0.006
	22	11,000	160	0.003	9,000	100	0.002	13,000	190	0.003
	25	10,000	120	0.002	8,500	80	0.002	12,000	140	0.002
1.2	30	10,000	80	0.002	8,500	50	0.002	12,000	100	0.002
	4	23,000	1,200	0.06	20,000	800	0.05	27,000	1,400	0.07
	6	20,000	900	0.05	18,000	600	0.04	25,000	1,200	0.06
	8	18,000	800	0.04	15,000	500	0.03	22,000	1,000	0.05
	10	16,000	700	0.03	14,000	450	0.02	20,000	850	0.04
	12	14,000	600	0.025	12,000	350	0.018	17,000	700	0.03
	16	12,000	400	0.015	10,000	250	0.01	14,000	450	0.02
1.4	20	10,000	300	0.01	8,000	180	0.007	12,000	360	0.012
	6	20,000	1,200	0.07	16,000	720	0.06	24,000	1,500	0.08
	8	18,000	1,000	0.06	14,000	580	0.05	22,000	1,300	0.07
	10	16,000	850	0.05	13,000	520	0.04	20,000	1,100	0.06
	12	14,000	700	0.04	12,000	450	0.03	17,000	850	0.05
	14	13,000	600	0.035	11,000	350	0.025	15,000	700	0.04
	16	12,000	500	0.025	10,000	300	0.018	13,000	550	0.03
1.5	22	10,000	350	0.015	8,000	210	0.01	10,000	350	0.012
	4	22,000	1,400	0.09	18,000	860	0.08	26,000	1,700	0.1
	6	20,000	1,200	0.08	16,000	720	0.07	24,000	1,500	0.09
	8	18,000	1,000	0.07	14,000	580	0.06	22,000	1,300	0.08
	10	16,000	850	0.06	13,000	520	0.05	20,000	1,100	0.07
	12	14,000	700	0.05	12,000	450	0.04	17,000	850	0.06
	14	13,000	600	0.04	11,000	380	0.03	16,000	750	0.05
	16	12,000	500	0.035	10,000	320	0.025	15,000	650	0.04
	18	11,000	450	0.03	9,000	280	0.02	13,000	530	0.035
	20	10,000	400	0.02	8,000	240	0.014	12,000	480	0.025
	25	9,000	350	0.015	7,000	200	0.01	9,000	350	0.018
	30	8,000	300	0.008	6,000	170	0.005	8,000	300	0.01
	35	7,000	200	0.005	5,500	130	0.003	7,000	200	0.006
	38	6,700	170	0.003	5,200	110	0.002	6,700	170	0.003
	40	6,500	150	0.002	5,000	90	0.002	6,500	150	0.002
	45	6,000	100	0.002	4,500	60	0.002	6,000	100	0.002
1.6	6	20,000	1,200	0.09	16,000	720	0.08	24,000	1,500	0.1
	8	18,000	1,000	0.08	14,000	580	0.07	22,000	1,300	0.09
	10	16,000	850	0.07	13,000	520	0.06	20,000	1,100	0.08
	12	14,000	700	0.06	12,000	450	0.05	18,000	900	0.07
	14	13,000	600	0.05	11,000	380	0.04	16,000	750	0.06
	16	12,000	500	0.04	10,000	320	0.03	14,000	620	0.05
	18	11,000	450	0.03	9,000	280	0.025	13,000	530	0.035
	20	10,000	400	0.025	8,000	240	0.018	12,000	480	0.03
	26	9,000	350	0.02	7,000	200	0.014	9,000	350	0.025

*1 切削合金钢、不锈钢时，请将主轴转速及进给速度降低至80%时的值作为参考值。

*1 Reference value for Alloy and Stainless Steels are 80% of recommended cutting conditions.

P 碳素钢
Carbon SteelP 合金钢
Alloy SteelP 调质钢
Prehardened SteelH ~52高硬度钢
HRC Hardened SteelM 不锈钢
Stainless SteelN 铝合金
Aluminium AlloyN 铜合金
CopperO 树脂
Resin

常规系列
无限涂层
长颈造型
Regular Line
MUGEN COATING
Long Neck Type

MHR230

切削参数参考表

Recommended Milling Conditions

加工材料 Work Material		碳素钢・合金钢* ₁ ・不锈钢* ₁ Carbon Steels・Alloy Steels* ₁ ・Stainless Steels* ₁ S50C・SCM* ₁ ・SKD* ₁ ・SUS* ₁			调质钢 Prehardened Steels NAK55・NAK80・HPM1 (~43HRC)			铜合金・铝合金 Copper・Aluminium Alloy		
外径 Dia.	颈长 Under Neck Length	主轴转速 Spindle Speed	进给速度 Feed	切深量 Depth of Cut	主轴转速 Spindle Speed	进给速度 Feed	切深量 Depth of Cut	主轴转速 Spindle Speed	进给速度 Feed	切深量 Depth of Cut
		min ⁻¹	mm/min	ap mm	min ⁻¹	mm/min	ap mm	min ⁻¹	mm/min	ap mm
1.8	6	18,000	1,300	0.1	14,000	760	0.09	22,000	1,600	0.12
	8	18,000	1,100	0.09	14,000	640	0.08	22,000	1,400	0.11
	10	16,000	900	0.08	13,000	550	0.07	20,000	1,200	0.1
	12	14,000	750	0.07	12,000	480	0.06	17,000	900	0.085
	14	13,000	650	0.06	11,000	420	0.05	16,000	800	0.07
	16	12,000	550	0.05	10,000	350	0.04	15,000	700	0.06
	18	11,000	500	0.04	9,000	310	0.03	13,000	600	0.05
	20	10,000	450	0.035	8,000	270	0.025	12,000	540	0.04
2	25	9,000	400	0.025	7,000	230	0.018	11,000	480	0.03
	4	16,000	1,500	0.13	13,000	900	0.12	20,000	1,850	0.15
	6	16,000	1,400	0.12	13,000	850	0.1	20,000	1,750	0.14
	8	16,000	1,300	0.11	13,000	800	0.09	20,000	1,650	0.13
	10	16,000	1,200	0.1	13,000	750	0.08	20,000	1,500	0.12
	12	14,000	1,000	0.09	12,000	650	0.07	17,000	1,200	0.11
	14	13,000	900	0.08	11,000	570	0.06	16,000	1,100	0.1
	16	12,000	800	0.07	10,000	500	0.05	15,000	1,000	0.085
	18	11,000	700	0.06	9,000	430	0.04	13,000	800	0.07
	20	10,000	600	0.05	8,000	360	0.035	12,000	720	0.06
	25	9,000	500	0.03	7,000	300	0.02	11,000	600	0.035
	30	8,000	400	0.02	6,000	220	0.014	9,000	450	0.025
	35	7,000	300	0.01	5,500	180	0.007	7,000	300	0.012
	40	6,000	200	0.005	5,000	140	0.003	6,000	200	0.006
	50	5,000	150	0.003	4,000	90	0.002	5,000	150	0.003
	60	4,500	100	0.002	3,500	60	0.002	4,500	100	0.002
2.5	8	13,000	1,400	0.15	11,000	900	0.12	16,000	1,700	0.18
	10	13,000	1,300	0.14	11,000	800	0.11	16,000	1,600	0.17
	12	13,000	1,200	0.13	11,000	750	0.1	16,000	1,500	0.16
	14	12,000	1,000	0.12	10,000	650	0.09	14,000	1,200	0.15
	16	11,000	900	0.1	9,000	550	0.07	13,000	1,100	0.12
	18	10,000	800	0.09	8,000	480	0.06	12,000	950	0.11
	20	9,000	700	0.08	7,000	400	0.05	11,000	850	0.1
	25	8,000	600	0.05	6,000	330	0.035	10,000	750	0.06
	30	7,000	500	0.03	5,500	280	0.02	8,500	600	0.035
	40	6,000	300	0.015	4,500	180	0.01	6,000	300	0.018
	50	5,000	200	0.01	4,000	120	0.007	5,000	200	0.012
	8	11,000	1,500	0.2	9,000	1,000	0.16	13,000	1,800	0.24
	10	11,000	1,400	0.18	9,000	900	0.14	13,000	1,700	0.22
	12	11,000	1,300	0.16	9,000	800	0.12	13,000	1,600	0.2
	14	11,000	1,200	0.14	9,000	700	0.1	13,000	1,400	0.17
3	16	10,000	1,000	0.12	8,000	600	0.09	12,000	1,200	0.15
	18	10,000	900	0.11	8,000	550	0.08	12,000	1,100	0.13
	20	9,000	800	0.1	7,000	450	0.07	11,000	1,000	0.12
	25	8,000	700	0.08	6,000	380	0.06	10,000	900	0.1
	30	7,000	600	0.06	5,000	300	0.045	8,500	730	0.07
	35	6,000	500	0.03	4,500	260	0.02	7,200	600	0.035
	40	5,000	400	0.025	4,000	220	0.018	6,000	480	0.03
	50	4,500	300	0.015	3,500	180	0.01	4,500	300	0.018

*1 切削合金钢、不锈钢时，请将主轴转速及进给速度降低至80%时的值作为参考值。

*1 Reference value for Alloy and Stainless Steels are 80% of recommended cutting conditions.

碳素钢
Carbon Steel P

合金钢
Alloy Steel P

调质钢
Prehardened Steel P

高硬度钢~52
Hardened Steel HRC H

不锈钢
Stainless Steel M

铝合金
Aluminium Alloy N

铜合金
Copper N

树脂
Resin O

常规系列
无限涂层
长颈造型
Regular Line
MUGEN COATING
Long Neck Type



切削参数参考表

Recommended Milling Conditions

加工材料 Work Material		碳素钢 · 合金钢 ^{※1} · 不锈钢 ^{※1} Carbon Steels · Alloy Steels ^{※1} · Stainless Steels ^{※1} S50C · SCM ^{※1} · SKD ^{※1} · SUS ^{※1}			调质钢 Prehardened Steels NAK55 · NAK80 · HPM1 (~43HRC)			铜合金 · 铝合金 Copper · Aluminium Alloy		
外径 Dia.	颈长 Under Neck Length	主轴转速 Spindle Speed	进给速度 Feed	切深量 Depth of Cut	主轴转速 Spindle Speed	进给速度 Feed	切深量 Depth of Cut	主轴转速 Spindle Speed	进给速度 Feed	切深量 Depth of Cut
		min ⁻¹	mm/min	ap mm	min ⁻¹	mm/min	ap mm	min ⁻¹	mm/min	ap mm
4	12	8,000	1,500	0.3	6,000	850	0.25	10,000	1,900	0.36
	16	8,000	1,400	0.25	6,000	800	0.2	10,000	1,800	0.3
	20	8,000	1,300	0.2	6,000	730	0.15	10,000	1,600	0.24
	25	7,000	1,100	0.15	5,000	600	0.1	8,500	1,300	0.18
	30	7,000	1,000	0.12	5,000	540	0.08	8,500	1,200	0.15
	35	6,000	800	0.1	4,500	450	0.07	7,200	1,000	0.12
	40	5,000	600	0.08	4,000	360	0.06	6,000	720	0.1
	45	4,500	500	0.06	3,500	300	0.04	5,400	600	0.07
	50	4,000	400	0.04	3,000	220	0.03	4,800	480	0.05
5	60	3,500	300	0.02	2,500	160	0.014	4,200	360	0.025
	16	6,000	1,400	0.35	4,500	800	0.3	7,200	1,700	0.42
	20	6,000	1,300	0.3	4,500	730	0.25	7,200	1,600	0.36
	25	6,000	1,200	0.25	4,500	680	0.2	7,200	1,500	0.3
	30	5,000	900	0.2	4,000	540	0.15	6,000	1,100	0.24
	35	5,000	800	0.15	3,500	420	0.1	6,000	1,000	0.18
	40	4,000	600	0.1	3,000	340	0.07	4,800	720	0.12
	50	3,500	450	0.07	2,500	240	0.05	4,200	540	0.085
	60	3,000	350	0.04	2,200	200	0.03	3,600	420	0.05
6	20	5,000	1,200	0.4	3,500	630	0.35	6,000	1,500	0.48
	30	4,000	900	0.35	3,000	500	0.3	4,800	1,100	0.42
	40	3,500	650	0.25	2,700	380	0.2	4,200	780	0.3
	50	3,000	500	0.15	2,200	280	0.1	3,600	600	0.18
	60	2,700	400	0.05	2,000	220	0.04	3,200	480	0.06
备 注 Notes		※1 切削合金钢、不锈钢时，请将主轴转速及进给速度降低至80%时的值作为参考值。 ※2 本切削参数仅供参考。请根据实际的加工形状和所使用的机床等调整切削参数。 ※3 切深量的ap表示轴向切深量。 ※4 请在考虑加工材料及加工形状等的基础上，选用合适的切削油。 ※5 加工深沟时，请充分注意切削油的供油及排屑是否顺畅。 ※6 轴向进刀建议采用倾斜进刀方式。 ※7 建议采用来回切削加工方式。 ※8 L（颈长）/D（外径）为5倍以上时，建议先使用颈长较短的刀具切削初期定位槽。 ※9 发生振刀时，请以相同的比率降低主轴转速和进给速度。此外，主轴转速过低时，也以相同的比率降低。 ※10 φ0.5以下或L（颈长）/D（外径）为15倍以上时，根据加工形状及使用机床等，有时必须对加工参数进行大幅调整。 ※11 刀具的伸出量超过柄径的5倍时，受铣刀刀柄跳动精度等的影响，有时必须对加工参数进行大幅调整。 此时请按相同的比率降低主轴转速和进给速度等，调整切削参数。 ※1 Reference value for Alloy and Stainless Steels are 80% of recommended cutting conditions. ※2 These recommended cutting conditions indicate just reference. It should be adjusted according to milling shape and machine type. ※3 ap:Axial Depth of Cut. ※4 Select a cutting fluid appropriate to work material, milling shape and machining content. ※5 Coolant supply and chip disposal in the deep portion are very important. ※6 Recommend to apply ramping for approaching into axial direction. ※7 Recommend reciprocating cutting. ※8 Recommend guide slotting process with short neck tool before milling with L/D 5 times or longer neck tool. ※9 Reduce both spindle speed and feed at same rate for chattering and also for insufficient spindle speed of a machine. ※10 Major adjustment of milling conditions appropriately on milling profile, machine tool and etc. required for the tools smaller than Dia. 0.5mm, or L/D 15 times longer. ※11 Major adjustment of milling conditions, e.g. adjust spindle and feed speed at same rate, required on condition of a tool overhang length exceeding a shank diameter 5 times due to possible accuracy impact by chuck runout etc.								

P 碳素钢
Carbon SteelP 合金钢
Alloy SteelP 调质钢
Prehardened SteelH ~52高硬度钢
HRC Hardened SteelM 不锈钢
Stainless SteelN 铝合金
Aluminium AlloyN 铜合金
CopperO 树脂
Resin